





XQU-CHR-43037
Bib Tap With Wall Flange
6.97 LPM @ 3 bar
0.5 Bar - 5 Bar
"Brass Ingots as per IS:1264-1997 Cu (58.0-63.0), Sn (0.0-1.0), Pb (0.5-2.5), Ni (0.0-1.0), Al (0.2-0.8), Mn (0.0-0.5), Total Impurity (0.0-2.0), Zn (Remainder)
Brass Rod as per IS:319-1989 Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)  Brass Sheets as per IS:410-1977 Cu (61.5-64.5), Pb (0.0-0.3), Fe (0.0-0.075), Total Impurity (0.0-0.6), Zn (Remainder)"
"Life Cycle EN 200: 200,000 cycles (Standard) - 5.0 LAC Cycles as per EN 200*"
16 bar (Pass)
25 bar (Pass)
"Plating: Nickel-13.0 micron Chromium-0.40 micron Salt Spray (700 hrs + Validated) Adhesion (Pass)"
CHROME (CHR)

<sup>\*</sup> As per in-house testing done on automatic life cycle testing machine made by Giussain, Italy

DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due to requirements in different sites, markets and/ or countries. 10% variation in flow rate may be possible. Jaquar reserves the right to make the necessary amendments at any time without prior notice.